

553,473

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
28 October 2004 (28.10.2004)


PCT

(10) International Publication Number
WO 2004/091846 A1

- (51) International Patent Classification⁷: **B23K 35/14**, C22C 21/00, C23C 8/08, F28D 9/00, F28F 19/04, 21/08
- (21) International Application Number: PCT/JP2004/005401
- (22) International Filing Date: 15 April 2004 (15.04.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
2003-111952 16 April 2003 (16.04.2003) JP
60/465,787 28 April 2003 (28.04.2003) US
- (71) Applicant (for all designated States except US): **SHOWA DENKO K.K.** [JP/JP]; 13-9, Shiba Daimon 1-chome Minato-ku Tokyo, 1058518 (JP).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): **USUI, Tadashi** [JP/JP]; c/o SHOWA DENKO K.K., OYAMA REGIONAL OFFICE, 480, Inuzuka 1-chome Oyama-shi Tochigi, 3238678 (JP).
- (74) Agents: **HIBI, Norihiko** et al.; c/o KISHIMOTO & CO. 3rd Floor, Inaba Building, 13-18, Nishishinsaibashi 1-chome, Chuo-ku Osaka-shi Osaka, 5420086 (JP).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report

[Continued on next page]

(54) Title: HEAT EXCHANGER AND PROCESS FOR FABRICATING SAME



(57) Abstract: A flat hollow body having a fluid channel inside thereof is made from two plates 2 serving as heat exchanger components, by brazing the plates at the peripheral edge portions thereof. The plate 2 comprises a core layer 21 of aluminum or aluminum alloy, and an Al-Si alloy layer 22 covering each of opposite sides of the core layer 21. The core layer 21 contains Si diffusing thereinto from the Al-Si alloy layer 22. The alloy layer 22 has a portion up to 1.65 mass % in Si content. The flat hollow body has high corrosion resistance.

WO 2004/091846 A1



For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.